



IFW

PTO/SB/21 (09-04)

Approved for use through 07/31/2006. OMB 0651-0031

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

TRANSMITTAL FORM

(to be used for all correspondence after initial filing)

Total Number of Pages in This Submission

21

Application Number

10/740,250

Filing Date

December 18, 2003

First Named Inventor

Hung Dang Ngoc

Art Unit

1713

Examiner Name

Kelechi C. Egwim

Attorney Docket Number

E-2-A

ENCLOSURES (Check all that apply)

<input type="checkbox"/> Fee Transmittal Form	<input type="checkbox"/> Drawing(s)	<input type="checkbox"/> After Allowance Communication to TC
<input type="checkbox"/> Fee Attached	<input type="checkbox"/> Licensing-related Papers	<input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences
<input type="checkbox"/> Amendment/Reply	<input type="checkbox"/> Petition	<input type="checkbox"/> Appeal Communication to TC (Appeal Notice, Brief, Reply Brief)
<input type="checkbox"/> After Final	<input type="checkbox"/> Petition to Convert to a Provisional Application	<input type="checkbox"/> Proprietary Information
<input type="checkbox"/> Affidavits/declaration(s)	<input type="checkbox"/> Power of Attorney, Revocation	<input type="checkbox"/> Status Letter
<input type="checkbox"/> Extension of Time Request	<input type="checkbox"/> Change of Correspondence Address	<input type="checkbox"/> Other Enclosure(s) (please identify below):
<input type="checkbox"/> Express Abandonment Request	<input type="checkbox"/> Terminal Disclaimer	
<input type="checkbox"/> Information Disclosure Statement	<input type="checkbox"/> Request for Refund	
<input checked="" type="checkbox"/> Certified Copy of Priority Document(s)	<input type="checkbox"/> CD, Number of CD(s) _____	
<input type="checkbox"/> Reply to Missing Parts/ Incomplete Application	<input type="checkbox"/> Landscape Table on CD	
<input type="checkbox"/> Reply to Missing Parts under 37 CFR 1.52 or 1.53		

Remarks

A certified copy of European Patent Application No. 02293160.4 is attached hereto.

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT

Firm Name			
Signature			
Printed name	Alvin T. Rockhill		
Date	April 11, 2005	Reg. No.	30,417

CERTIFICATE OF TRANSMISSION/MAILING

I hereby certify that this correspondence is being facsimile transmitted to the USPTO or deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450 on the date shown below:

Signature			
Typed or printed name	Mary A. Nicoloff	Date	April 11, 2005

This collection of information is required by 37 CFR 1.5. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.11 and 1.14. This collection is estimated to 2 hours to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.



THIS PAGE BLANK (USPTO)



**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02293160.4

**CERTIFIED COPY OF
PRIORITY DOCUMENT**

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

THIS PAGE BLANK (USPTO)



Anmeldung Nr:
Application no.: 02293160.4
Demande no:

Anmeldetag:
Date of filing: 19.12.02
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Eliokem
14, Avenue des Tropiques,
ZA de Courtaboeuf 2
91140 Villejust
FRANCE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se referer à la description.)

Rubbery polymer with improved properties

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

C08L33/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SI SK

THIS PAGE BLANK (CONT.)

5 The present invention relates to a rubbery polymer
which can be blended with polyvinylchloride (PVC),
halogen containing polymers, Polyurethanes, styrenic
polymers (polymers which contain styrene such as
acrylonitrile butadiene styrene (ABS), acrylonitrile
10 styrene acrylate (ASA), styrene ethylene butadiene
styrene (SEBS), etc.), Polyesters and copolymers ester-
ether (COPE), Polyamides, Polycarbonates, as well as
Polyolefins via compatibilization techniques to make
leathery compositions.

15 Automotive instrument panels and door panels are
typically composites which are made of a rigid backing
which supports a semi-rigid urethane foam with the semi-
rigid urethane foam being covered with a skin compound.
Such skin compounds are typically blends of polyvinyl
20 chloride (PVC) with a nitrile rubber (NBR).

The nitrile rubber is included in such blends as a
permanent modifier for the PVC which provides it with a
higher degree of flexibility.

The automotive industry is currently moving toward
25 more aerodynamic body designs which typically include
larger glass areas. Such design changes have
significantly increased the heat and ultraviolet light
aging requirements of automotive interiors. This has in
turn significantly increased the demands put upon the
30 polymers which are utilized as skins in automotive
interior panels.

Heat and light stabilizers can be employed to improve the heat and ultraviolet light aging characteristics of conventional PVC/NBR blends which are utilized as skins for automotive interior panels.

5 However, the degree to which the aging characteristics of such blends can be improved by the addition of additives is limited. In fact, there is a demand for performance characteristics in such applications which theretofore has not been realized by
10 the utilization of heat and light stabilizers. For instance, it would be highly desirable for the skins used in automotive panels to resist discoloration and cracking under conditions of high heat and intense ultraviolet light throughout the life of the vehicle.

15 NBR/PVC blends offer an array of physical properties which make them useful as a skin composition for automotive panels. The NBR acts as a permanent flexibilizing polymer for the PVC. It also acts as a shrinkage control agent, and embossing aid, and improves
20 grain retention. The NBR in such blends further provides vacuum forming gauge control and exhibits low fog characteristics. NBR is highly compatible with PVC and has the capability of being recycled. It is essential for any polymer which is substituted for NBR to display these
25 essential characteristics.

US Patent 5,380,785, US patent 5,415,940, US patent 5,504,155, US patent 5,504,160 and US patent 5,616,651 disclose a rubbery polymer which can be blended with PVC to make leathery compositions. These compositions are
30 particularly useful in manufacturing skins for automotive interior paneling. Skin compositions, which are made utilizing this rubbery polymer, provide a higher level of

resistance to heat and ultraviolet light than those made utilizing conventional NBR/PVC blends. The rubbery polymers of United States Patent 5,380,785 also offer low fog characteristics, low odor, shrinkage control, and grain retention. They also act as an embossing aid and as a permanent flexibilizing modifier. These rubbery polymers also have characteristics which make them useful in building gasket applications.

US patent 5,380,785 also specifically discloses a rubbery polymer which can be blended with polyvinyl chloride to make leathery compositions having good heat and ultraviolet light resistance, said rubbery polymer being comprised of repeat units which are comprised of (a) butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) acrylonitrile, (d) styrene, (e) a half ester maleate soap, and (f) a crosslinking agent.

Polymers of this general type are sold by the Eliokem Company as Sunigum[®] rubber.

US patent 5,962,591, discloses that blends of certain rubbery polymers with polyolefins can be compatibilized with ethylene alkyl acrylates or ethylene vinyl acetate. These blends can be made so as to be useful as skins for automotive interior panels and can be made so as to be leathery in nature.

The compositions according to the invention are particularly useful in manufacturing skins for automotive interior paneling. Skin compositions which are made utilizing this rubbery polymer provide a higher level of

resistance to heat and ultraviolet light than those made utilizing conventional NBR/PVC blends. The rubbery polymers of this invention also offer low fog characteristics, low odor, shrinkage control, and grain retention. They also act as an embossing aid and as a permanent flexibilizing modifier. The rubbery polymers of this invention also have characteristics which made them useful in building gasket applications.

The present invention discloses a rubbery polymer which can be blended with PVC, halogen containing polymers, Polyurethanes, styrenic polymers (polymers which contain styrene such as ABS, ASA, SEBS, etc.), Polyesters and copolymers ester-ether (COPE), Polyamides, Polycarbonates, as well as Polyolefins via compatibilization techniques to make leathery compositions having good heat and ultraviolet light resistance, said rubbery polymer being comprised of repeat units which are comprised of (a) butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl me(acrylate), (d) acrylonitrile, (e) styrene, and (f) a crosslinking agent; wherein about 1 to about 10% of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

Advantageously, such rubbery polymers contain repeat units (chain linkages) which are derived from (a) butyl

acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl me(acrylate), (d) acrylonitrile, (e) styrene, and (f) a crosslinking agent; wherein (g) about 1 to about 10% of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

These repeat units differ from the monomers that they were derived from in that they contain one less carbon-carbon double bond than it is present in the respective monomer. In other words, a carbon-to-carbon double bond is consumed during the polymerization of the monomer into a repeat unit in the rubbery polymer. Thus, in saying that the rubbery polymer contains various monomers in actuality means that it contains repeat units which are derived from those monomers.

The rubbery polymers, which are modified in accordance with this invention, will normally contain (a) from about 40 to about 80% by weight butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to 40% by weight 2-ethylhexyl acrylate, (b) from about 5 to about 35% by weight methyl methacrylate, ethyl methacrylate, methyl acrylate, or ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl me(acrylate), (d) from about 4 to about 30% by weight acrylonitrile, (e) from about 3 to about 25% by weight styrene, (f) from about 0.25 to about 8% by weight

of a crosslinking agent wherein (g) from about 0.1 to about 10% by weight of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated
5 during emulsion polymerization onto said rubbery polymer.

Such rubbery polymers will preferably contain (a) from about 50 to about 80% by weight butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl
10 acrylate, (b) from about 3 to about 25% by weight of at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl me(acrylate), (d) from about 6 to about
15 30% by weight acrylonitrile, (e) from about 5 to about 18% by weight styrene, (f) from about 0.5 to about 4% by weight of a crosslinking agent wherein (g) from about 1 to about 8% by weight of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic
20 acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

The rubbery polymer will more preferably be comprised of repeat units which are derived from (a) from about 55 to about 75% by weight butyl acrylate, or optionally a
25 mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) from about 5 to about 20% by weight of at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and
30 ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl me(acrylate), (d) from about 10 to about 25% by weight acrylonitrile, (e) from about 8 to about 14% by

weight styrene, (f) from about 1 to about 3% by weight of a crosslinking agent wherein (g) from about 2 to about 6% by weight of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

Variety of reactive cure site (co)monomers can be used in carrying out the polymerizations to produce the rubbery polymer.

Some representative examples of reactive cure site which can be utilized include carboxy derivatives such as acrylic or methacrylic acid, maleic acid, fumaric acid and itaconic acid; hydroxy derivatives such as 2-hydroxyethyl (me)acrylate, 2-hydroxypropyl (me)acrylate, 3-hydroxypropyl (me)acrylate, 2-hydroxyethyl crotonate, pentahydroxyethyl (me)acrylate, 2,3,4,5-tetrahydroxypentyl (me)acrylate, etc. The particularly preferable ones are (me)acrylic acid and 2-hydroxyethyl (me)acrylate.

Some representative examples of glycidyl derivatives which can be utilized include glycidyl (me)acrylate, allyl glycidyl ether, itaconic acid monoglycidyl ester, butenetricarboxylic acid monoglycidyl ester, butenetricarboxylic acid diglycidyl ester, butenetricarboxylic acid triglycidyl ester, vinyl glycidyl ethers and esters of maleic acid, fumaric acid and crotonic acid, etc. The particularly preferable ones are glycidyl (me)acrylate and allyl glycidyl ether.

Some representative examples of unsaturated cure site can be utilized include butadiene, isoprene, allyl maleate, tetrahydrobenzyl acrylate, diallyl phthalate, dicyclopentenyl acrylate, dicyclopentenylloxyethyl

methacrylate, etc. When the reactive cure site is an unsaturated cure site, sulfur vulcanisation with or without accelerator or other vulcanisation agents such as phenolic curatives, benzoquinone derivatives, metal
5 oxides, organic peroxides and bismaleimides can be used to improve the polymer network during processing as described by A.Y. Coran in *Encyclopedia of Polymer Science and Engineering*, **17** (Second Edition), 666-698. When the reactive cure sites are carboxy derivatives,
10 hydroxy derivatives or glycidyl derivatives, chemical reactions are more preferable to improve compatibilization or polymer network during processing or polymer blending.

The percentages reported in this paragraph are based upon the total weight of the rubbery polymer.

15 The present invention further reveals a leathery composition which is useful in automotive applications which is comprised of (1) a thermoplastic such as PVC, halogen containing polymers, Polyurethanes, styrenic polymers (polymers which contain styrene such as ABS,
20 ASA, SEBS, etc.), Polyesters and copolymers ester-ether (COPE), Polyamides, Polycarbonates, as well as Polyolefins via compatibilization techniques, (2) a plasticizer, and (3) a rubbery polymer which is comprised of (a) butyl acrylate, or optionally a mixture of butyl
25 acrylate and 2-ethylhexyl acrylate containing up to about 40 percent 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of
30 alkoxy ethyl me(acrylate), (d) acrylonitrile, (e) styrene, and (f) a crosslinking agent; wherein about 1 to about 10% of a reactive cure site (co)monomer containing

hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

These leathery compositions offer an excellent
5 combination of properties for utilization in making skin compounds for panels used in automotive applications. These leathery compositions can be prepared by blending the rubbery polymer into polyvinylchloride (PVC) utilizing standard mixing techniques. It is highly
10 preferred for the improved rubbery polymer of this invention to be in powdered form when blended into PVC to make such leathery compositions.

A wide variety of plasticizers which are compatible with the polyvinyl chloride resins can be employed.

15 Such leathery compositions typically contain from about 40 to 160 parts by weight of the improved rubbery polymer of this invention, from about 10 to about 50 parts of a plasticizer, and from about 0.1 to about 5 parts by weight of an antidegradant per 100 parts by
20 weight of the polyvinylchloride. It is typically preferred for such leathery compositions to contain from about 60 to about 120 parts by weight of the improved rubbery polymer of this invention, from about 15 to about 40 parts of the plasticizer, and from about 0.5 to 3
25 parts of an antidegradant (per 100 parts of the PVC). It is typically more preferred for the leathery composition to contain from about 70 to about 90 parts by weight of the improved rubbery polymer of this invention, from about 20 to about 30 parts by weight of the plasticizer,
30 and from about 1 to 2 parts by weight of the antidegradant per 100 parts by weight of the PVC.

Such compositions will also generally contain an acrylonitrile-butadiene-styrene resin (ABS resin).

The leathery composition will typically contain from about 15 parts to about 80 parts of ABS resin per 100 parts of PVC. The leathery composition will preferably contain from about 25 to about 55 parts per weight of the ABS resin per 100 parts by weight of the PVC. It is generally more preferred for the leathery composition to contain from about 30 to about 40 parts by weight of the ABS resin per 100 parts by weight of PVC. Various colorants and/or pigments will typically also be added to the composition to attain a desired color.

The leathery compositions of this invention are useful in a wide variety of applications. For example, they have been found to be extremely valuable when used in making skins for automotive panels. Such panels are typically comprised of a semi-rigid urethane foam which is supported by a rigid backing and covered with the leathery composition of this invention. Such skins are made by calendaring the leathery compositions of this invention and then cutting them to the desired size and shape. Such skins for automotive applications which are made with the leathery compositions of this invention offer outstanding heat and ultraviolet light stability.

These are highly desirable characteristics which can help to prevent the skin of automotive panels from cracking during the normal life of the vehicle.

The improved rubbery polymers of this invention can also be blended with other halogen containing polymers (in addition to PVC), styrenic polymers (polymers which contain styrene, such as acrylonitrile-styrene-acrylate (ASA) polymers, ABS, SEBS polymers, etc.), polyesters and

copolyester-ether, polycarbonates, polyamides, polyurethanes, polyolefins to produce compositions which exhibit good heat and ultraviolet light resistance. Such polymeric compositions can be used in manufacturing a wide variety of useful articles, such as profiles, moldings, sheeting, flooring, wall coverings, hose, cables, and footwear. Virtually any type of polyamide (nylon) can be utilized in preparing such blends. These nylons are generally prepared by reacting diamines with dicarboxylic acids. The diamines and dicarboxylic acids which are utilized in preparing such nylons will generally contain from about 2 to about 12 carbon atoms. However, nylons which can be utilized in such blends can also be prepared by addition polymerization. Some representative examples of nylons which can be used include nylon-6,6, nylon-6, nylon-7, nylon-8, nylon-9, nylon-10, nylon-11, nylon-12 and nylon-6,12. Some representative examples of polyolefins which can be used include low density polyethylene, linear low density polyethylene, high density polyethylene, polypropylene, metallocene catalyzed polyolefins, and modified polyolefins, such as ethylene vinyl acetate (EVA), ethylene-alkyl (Me)acrylate or terpolymers of ethylene, alkyl (Me)acrylate and acrylic acid.

The present invention further discloses a process for preparing a rubbery polymer which can be blended with PVC, halogen containing polymers, Polyurethanes, styrenic polymers (polymers which contain styrene such as ABS, ASA, SEBS, etc.), Polyesters and copolymers ester-ether (COPE), Polyamides, Polycarbonates, as well as Polyolefins via compatibilization techniques to make leathery compositions having good heat and ultraviolet

light resistance, said process comprising the steps of (1) polymerizing (a) butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl me(acrylate), (d) acrylonitrile, and (e) a crosslinking agent; wherein about 1 to about 10% of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated under emulsion polymerization conditions to produce a seed polymer containing latex; (2) adding (a) styrene, (b) additional acrylonitrile, and (c) additional crosslinking agent to the seed polymer containing latex under emulsion polymerization conditions which result in the formation of an emulsion containing the rubbery polymer; (3) recovering the rubbery polymer from the emulsion containing the rubbery polymer.

The rubbery polymers, which are modified in accordance with the process of present invention, are synthesized in an aqueous reaction mixture by utilizing a free radical polymerization technique.

The reaction mixture utilized in this polymerization technique is comprised of water, the appropriate monomers, a suitable free radical initiator, a crosslinking agent, and a soap.

A wide variety of soap can be utilized in carrying out the polymerizations to produce the rubbery polymer. Some representative examples of soap which can be utilized include the half ester maleate soap, and/or the

metal salt of an alkyl sulfonate or the metal salt of an alkyl sulfate.

The half ester maleate soap utilized in the polymerization is prepared by reacting maleic anhydride with a fatty alcohol containing from about 10 to about 24 carbon atoms. It is typically preferred to utilize a fatty alcohol which contains from about 12 to about 16 carbon atoms. One mole of the maleic anhydride is reacted with one mole of the fatty alcohol in producing the half ester maleate soap. This reaction is typically conducted at a temperature that is within the range of about 50 to about 80°C. Sodium hydroxide or potassium hydroxide is then added to make the half ester maleate soap.

Some representative examples of sulfonate and sulfate surfactants which can be used include sodium toluenexylene sulfonate, sodium toluene sulfonate, sodium cumene sulfonate, sodium decyldiphenyl ether sulfonate, sodium dodecylbenzenesulfonate, sodium dodecyldiphenylether sulfonate, sodium 1-octane sulfonate, sodium tetradecane sulfonate, sodium pentadecane sulfonate, sodium heptadecane sulfonate. Metal salts of alkylbenzene sulfonates are a highly preferred class of sulfonate surfactant. The metal will generally be sodium or potassium.

The sulfonate surfactant can be a mixture of (mono)dialkylate ether disulfonates. The advantage of the disulfonate structure is that it contains two ionic charges per molecule instead of one as in the case with conventional alkyl sulfonate surfactants.

The sulfate surfactants, which are useful in the practice of this invention, include metal salts of alkylsulfates having the structural formula ROSO_3X and

metal salts of alkylethersulfates having the structural formula $RO(CH_2CH_2O)_nSO_3X$, wherein R represents an alkyl group and wherein X represents sodium or potassium. Sodium lauryl sulfate, sodium ethanolamine lauryl sulfate, triethanolamine lauryl sulfate are representative examples of commercially available sulfate surfactants.

The reaction mixture utilized in this polymerization technique will normally contain from about 10 to about 80% by weight monomers, based upon the total weight of the reaction mixture. The reaction mixture will preferably contain from about 20 to about 70% by weight monomers and will more preferably contain from about 40 to about 50% by weight monomers.

The free radical emulsion polymerizations utilized in synthesizing the rubbery polymer are typically conducted at a temperature which is within the range of about 10 to about 95°C. In most cases, the polymerization temperature utilized will vary between about 20 and about 80°C. The polymerization is carried out as a two-step batch process. In the first step, a seed polymer containing latex is synthesized.

This is done by polymerizing (a) butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl methacrylate, (d) acrylonitrile, (e) a crosslinking agent wherein (f) about 1 to about 10% of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic

acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

The seed polymer containing latex is typically prepared by the polymerization of a monomer mixture which
5 contains about 40 to about 90% by weight butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, from about 5 to about 35% by weight methyl methacrylate, ethyl methacrylate, methyl acrylate,
10 or ethyl acrylate, from about 2 to about 30% by weight acrylonitrile, and from about 0.25 to 6% by weight of the crosslinking agent wherein from about 0.1 to about 10% by weight of a (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated
15 cure site is incorporated during emulsion polymerization, onto said rubbery polymer.

It is typically preferred for the monomeric component utilized in the first step to include about 50 to about 85% by weight butyl acrylate, or optionally a mixture of
20 butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, from about 5 to about 30% by weight ethyl acrylate, ethyl methacrylate, methyl acrylate, or methyl methacrylate, from about 4 to about 28% by weight acrylonitrile, and from about 0.5 to about
25 4% by weight of the crosslinking agent wherein (g) from about 0.1 to about 10% by weight of a (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

30 It is generally more preferred for the monomer charge composition used in synthesizing the seed polymer latex to contain from about 60 to about 80% by weight butyl

acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, from about 5 to about 25% by weight methyl methacrylate, ethyl methacrylate, methyl acrylate, or ethyl acrylate, from about 5 to about 25% by weight acrylonitrile, and from about 1 to about 3% by weight crosslinking agent wherein (g) from about 0.1 to about 10% by weight of a (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

After the seed polymer latex has been prepared, styrene monomer, additional acrylonitrile monomer, and additional crosslinking agent is added to the seed polymer containing latex. As a general rule, from about 4 parts by weight to about 30 parts by weight of styrene, from about 1 part by weight to about 20 parts by weight of additional acrylonitrile, and from about 0.01 to 2 parts by weight of the crosslinking agent will be added to the seed polymer per 100 parts dry weight of the seed polymer. In this second stage of the polymerization, it is preferred to add from about 6 parts by weight to about 22 parts by weight of styrene, from about 3 parts by weight to about 12 parts by weight of acrylonitrile, and from about 0.05 parts by weight to 1 part by weight of the crosslinking agent. It is typically more preferred for from about 10 parts by weight to about 17 parts by weight of styrene, from about 4 parts by weight to about 8 parts by weight of acrylonitrile, and from about 0.1 parts by weight to about 0.5 parts by weight of the crosslinking agent to be added to the seed polymer latex to initiate the second phase of the polymerization.

A wide variety of crosslinking agents can be utilized in carrying out the polymerizations to produce the rubbery polymer. Some representative examples of crosslinking agents which can be utilized include
5 difunctional acrylates, difunctional methacrylates, trifunctional acrylates, trifunctional methacrylates, and divinylbenzene. 1,4-butanediol dimethacrylate has proven to be particularly useful as the crosslinking agent.

The rubbery polymer can be made by the two-step
10 batch, semi-continuous or continuous emulsion polymerization process. In most cases, the polymerization will be continued until a high monomer conversion has been reached. At this point, the rubbery polymer made by the two-step polymerization process is recovered from the
15 emulsion (latex) after the optional deodorizing step. This can be accomplished by utilizing standard coagulation techniques. For instance, coagulation can be accomplished by the addition of salts, acids, or both to the latex.

20 After the rubbery polymer is recovered by coagulation, it can be washed to further reduce odors. This can be accomplished by simply pouring or spraying water on the rubbery polymer. The rubbery polymer can also be washed by putting it in a water bath which will
25 further reduce odor. After being washed, the rubbery polymer is generally dried. It is sometimes advantageous to convert the rubbery polymer into a powder to facilitate its usage. In this case, it will be beneficial to add a partitioning agent to the rubbery polymer. Some
30 representative examples of partitioning agents which can be employed include calcium carbonate, emulsion polyvinyl chloride, and silica. Calcium carbonate is a highly

desirable partitioning agent which can be utilized in such applications.

This invention is illustrated by the following examples which are merely for the purpose of illustration and are not to be regarded as limiting the scope of this invention or the manner in which it can be practiced. Unless specifically indicated otherwise, all parts and percentages are given by weight.

10 Example 1 (comparative example)

In this experiment, a rubbery polymer was made in a 10 litres stainless steel reactor. The reactor was equipped with an axially flow turbine agitator which was operated at 450 rpm (revolutions per minute).

15 The reactor was charged with 6348.68 g of water, 72.8 g of a half ester maleate soap (made with C₁₆ fatty alcohol), 2.73 g of sodium dodecylbenzenesulfonate, 31.2 g of a 50 percent aqueous potassium hydroxide solution, 5.2 g of sodium pyrophosphate, 1837.68 g of n-
20 butylacrylate, 218.4 g of acrylonitrile, 109.2 g of methylmethacrylate, 44.2 g of 1,4-butanediol dimethacrylate, 2.08 g of t-dodecylmercaptan, 1.56 g of triethanol amine, and 6.5 g of potassium persulfate were initially charged into the reactor. A temperature of
25 about 35°C was maintained during the first stage of the polymerization. When a solids content of about 20% was reached the reaction temperature was increased to about 60°C and a temperature of about 60°C was maintained throughout the polymerization until the total solids
30 content of about 25% was achieved. This first stage of polymerization was carried out for a period of about 2 hours and a half. This first stage polymerization

resulted in the production of seed polymer latex which was used in the second step of the polymerization.

In the second step of the polymerization, 124.8 g of acrylonitrile, 242 g of styrene, 4.68 g of
5 divinylbenzene, and 0.78 g of t-dodecylmercaptan were charged into the reactor containing the seed polymer latex. The polymerization proceeded until a solids content of about 30% was reached.

The latex made was subsequently coagulated and a dry
10 rubber was recovered.

Example 2

In this experiment, a rubbery polymer was synthesized in a 10 litres reactor utilizing the technique of this
15 invention. In the procedure employed 6348.68 g of water, 72.8 g of hexadecylmonomaleate, 9.1 g of a 30% solution of sodium dodecylbenzene sulfonate, 31.2 g of a 50% aqueous potassium hydroxide solution, 5.2 g of sodium pyrophosphate, 8.4 g of acrylonitrile, 4.2 g of methyl
20 methacrylate, 71.4 g of n-butyl acrylate, 39 g of glycidyl methacrylate, 26 g of 1,4-butanediol dimethacrylate, 2.08 g of t-dodecylmercaptan, 1.56 g of triethanol amine, and 6.5 g of potassium persulfate were initially charged into the reactor. A temperature of
25 about 35°C was maintained during the first stage of the polymerization. When a solids content of about 20% was reached the reaction temperature was increased to about 60°C and 124.8 g of additional acrylonitrile, 242 g of styrene, 4.88 g of divinylbenzene, and 0.78 g of t-
30 dodecylmercaptan were charged into the reactor.

After the polymerization was completed, the latex made was coagulated and a rubber was recovered.

Example 3

The procedure used in Example 2 was repeated in this experiment except that 44.2 g (instead of 26 g) of 1,4-butanediol dimethacrylate was charged into the reactor.

5

Example 4

The procedure used in Example 2 was repeated in this experiment, except that 44.2 g (instead of 26 g) of 1,4-butanediol dimethacrylate and 130 g of dicyclopentenylloxyethyl methacrylate (instead of 39 g of glycidyl methacrylate) were charged into the reactor.

10

Antioxydants such as Wingstay L[®], Wingstay K[®] in emulsion form or in dispersion form could be used to stabilize the rubbery polymer during drying and storage.

15 The latex made was subsequently coagulated and a dry rubber was recovered.

Example 5

20 The procedure used in Example 4 was repeated in this experiment, except that 130 g of diallyl phthalate has been used to replace dicyclopentenylloxyethyl methacrylate.

Examples 6-9

25 In these series of experiments, leathery compositions were made by blending the rubbery polymers made in Examples 1 and 3 or other rubbery polymers (Chemigum[®]) into PVC. In the procedure used 40 parts of the rubbery polymers was blended into 100 parts of the PVC. The
30 blends made also included 80 parts of DOP and 3 parts of Ba/Zn. The blends were made by mixing the components in a mill at 180°C for 6 minutes and then pressing them into

samples at 180°C. The samples made were then tested to determine their physical properties.

The physical properties of the samples made are reported in Table I. The blend made in Example 6 contained Eliokem Chemigum® P83, the blend of Example 7 contained Eliokem Chemigum® P35, the blend of Example 8 contained the rubber composition of Example 1, and the blend of Example 9 contained the rubber composition of Example 3.

As it can be seen in Table I, all the rubbery polymers made in Examples 1 and 3 could be made into leathery compositions, which had good physical properties compared to the Chemigum® nitrile rubber.

TABLE I

Examples	Shore A Hardness	Tensile Strength	Elongation	Modulus		Compression set 22h at 70°C
				50% MPa	100% MPa	
Example 6	64	13MPa	500%	3.3	5.8	58.2%
Example 7	64	9.7MPa	417%	2.8	4.9	51.4%
Example 8	65	11.8MPa	352%	2.2	4.5	56.9%
Example 9	65	10.9MPa	326%	2.3	4.5	56.4%

Examples 10-13

In these series of experiments, leathery compositions were made by blending the rubbery polymers made in Examples 1, 4 and 5 into PVC. The procedure of Examples 6-9 was repeated except 100 parts of the rubbery polymers was blended into 100 parts of the PVC.

The physical properties of the samples made are reported in Table II. The blend made in Example 10 contained the rubber composition of Example 1, the blend of Example 11 contained rubber composition of Example 4, the blend of Example 12 contained the rubber composition

of Example 5, and the blend of Example 13 contained the rubber composition of Example 4 and 10 parts of Lotader® AX 8900® per cent parts of the rubbery polymer as a crosslinking agent.

5

TABLE II

Examples	10	11	12	13
Hardness Shore A	56	56	57	57
Tensile Strength (MPa)	11.5	10	9.8	10.3
Elongation at break %	282	239	205	232
Modulus at 50% (MPa)	1.8	2.0	2.0	2.2
Modulus at 100% (MPa)	3.5	3.8	3.9	4.2
Tear Strength (kN/m)	23	19.2	19.4	20.6
Compression set 22hrs at 70°C	54.6	48.6	45	42

As it can be seen from Table II, the compression set behaviour of the blends made with the rubber composition polymer of this invention is better than did the control.

10 Examples 14-18

In these series of experiments, rubbery polymer was blended into metallocene catalyzed polyethylene. In the procedure, 60 parts of the rubbery polymer was blended at a temperature of 180°C with 40 parts of Engage® 8100 in a
 15 Haake Rheocord 90 operated at 60 rotations per minute over a period of 30 minutes. Blends were pressed into samples at 180°C. The samples were then tested to determine their physical properties.

The physical properties of the samples made are reported in Table III. The blend made in Example 14 contained rubber composition of Example 1. Example 15 was a compatibilized blend of the rubber composition of Example 1 and 10 parts of Lotader® 8900 percent parts of the rubber composition polymer. For comparative purposes,
 20 a second blend was made with the rubber composition of
 25

Example 3 without including the compatibilizing polymer in Example 16, or with 10 parts of Lotader® 8900 per cent parts of the rubber composition polymer in Example 17 or with 10 parts of Elvax® 360 per 100 parts of the rubber composition in Example 18.

TABLE III

Examples	14	15	16	17	18
Shore A Hardness	60	63	60	63	62
Tensile Strength (MPa)	4.3	6.6	4.1	10.4	4.8
Elongation at break (%)	700	500	475	490	750
Modulus at 50% (MPa)	1.7	1.9	1.6	1.9	1.8
Modulus at 100% (MPa)	2.6	2.8	2.5	3	2.7
Tear Strength (kN/m)	26	25	24	43	27

As it can be seen from Table III, physical properties of the blends made with the rubber composition polymer of this invention are better than did the control that did not contain glycidyl functional group monomer.

Examples 19-25

In these series of experiments, rubbery polymer was blended into high density polyethylene HDPE having melt flow index MFI about 4. In the procedure 70 parts of the rubbery polymer was blended at a temperature of 180°C with 30 parts of HDPE KS10100® from Dow Plastics in a Haake Rheocord 90 operated at 60 rpm over a period of 30 minutes. Blends were pressed into samples at 180°C. The samples were then tested to determine their physical properties.

The physical properties of the samples made are reported in Table IV. The blend made in Example 19 contained rubber composition of Example 1. Example 20 was a compatibilized blend of the rubber composition of Examples 1 and 10 parts of Elvax® 360, while Example 21

was a compatibilized blend of the rubber composition of Example 1 and 10 parts of Lotader® AX 8900. For comparative purpose, a second blend was made with the rubber composition of Example 2 without including the compatibilizing polymer in Example 22 or with 10 parts of Elvax® 360 per cent parts of the rubber composition in Example 23. Otherwise, Example 24 was the blend of Example 16 including 10 parts of Elvax® 670 and Example 25 was the blend of Example 16 including 10 parts of Lotader® AX8900.

TABLE IV

Examples	19	20	21	22	23	24	25
Tensile at break (MPa)	5.1	5.2	9.5	5.6	9.8	9.3	12.6
Elongation at break %	74	147	270	71	203	192	282
Modulus 50% (MPa)	5.4	5.1	6.4	5.2	6.6	6.5	6.3
Modulus 100% (MPa)	-	-	-	-	7.9	7.8	7.8
Tear strength kN/m	37	34	54	28	50	44	54

As it can be seen from Table IV, physical properties of compatibilized blends made with the rubber composition polymer of this invention are better than did the control that did not contain glycidyl functional group monomer.

Examples 26-29

In these series of experiments, same procedure as Examples 19-25 was used, except 40 parts of the rubbery polymer was blended with 60 parts of HDPE KS 10100 from Dow Plastics and 10 parts of compatibilizing polymer per 100 parts of the rubber composition polymer. Examples 26 and 27 were compatibilized blends of the rubber composition of Examples 1 and 2 respectively and 10 parts of Lotader® AX 8900 per cent parts of the rubber composition polymer. Examples 28 and 29 were compatibilized blends of the rubber composition of

Examples 1 and 2 respectively and 10 parts of Elvax® 360 per cent parts of the rubber composition polymer.

The physical properties of the samples made are reported in Table V.

5

TABLE V

Examples	26	27	28	29
Tensile at break (MPa)	8.7	12.6	10.4	12.7
Elongation at break %	287	367	51	184
Modulus 50% (MPa)	-	12.1	9.7	12.7
Modulus 100% (MPa)	-	12	-	12.6
Tear strength kN/m	113	112	69	80

As it can be seen in Table V, physical properties of the compatibilized blends made with the rubber composition polymer of this invention are better than did the control for both types of compatibilizing polymers Lotader® AX 8900 as well as Elvax® 360.

While certain representative embodiments and details have been shown for the purpose of illustrating the subject invention, it will be apparent to those skilled in this art that various changes and modifications can be made therein without departing from the scope of the subject invention.

THIS PAGE BLANK (USPTO)

Claims

1. A rubbery polymer having improved properties, which is comprised of repeat units which are comprised of (a) butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40 percent 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl (me)acrylate, (d) acrylonitrile, (e) styrene, and (f) a crosslinking agent; wherein about 1 to about 10% of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

2. A rubbery polymer as specified in claim 1, which is comprised of repeat units which are derived from about 40 to about 80% by weight butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to 40% by weight 2-ethylhexyl acrylate, (b) from about 5 to about 35% by weight methyl methacrylate, ethyl methacrylate, methyl acrylate, or ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl (me)acrylate, (d) from about 4 to about 30% by weight acrylonitrile, (e) from about 3 to about 25% by weight styrene, (f) from about 0.25 to about 8% by weight of a crosslinking agent wherein (g) from about 0.1 to about 10% by weight of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic

acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

3. A rubbery polymer as specified in anyone of claims 1
5 to 2, which preferably contains from about 50 to about 80% by weight butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) from about 3 to about 25% by weight of at least one member selected from
10 the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl me(acrylate), (d) from about 6 to about 30% by weight acrylonitrile, (e) from about 5 to about 18% by weight
15 styrene, (f) from about 0.5 to about 4% by weight of a crosslinking agent wherein (g) from about 1 to about 8% by weight of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion
20 polymerization onto said rubbery polymer.

4. A rubbery polymer as specified in anyone of claims 1 to 3, which is comprised of repeat units which are derived (a) from about 55 to about 75% by weight butyl
25 acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) from about 5 to about 20% by weight of at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate,
30 methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl me(acrylate), (d) from about 10 to about 25% by weight acrylonitrile, (e) from

about 8 to about 14% by weight styrene, (f) from about 1 to about 3% by weight of a crosslinking agent wherein (g) from about 2 to about 6% by weight of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

5. A rubbery polymer as specified in anyone of claims 1 to 4, wherein the reactive cure site (co)monomer containing hydroxyl groups is selected from the group consisting of hydroxyethyl acrylate or hydroxyethyl methacrylate.

6. A rubbery polymer as specified in anyone of claims 1 to 4, wherein the reactive cure site (co)monomer containing carboxylic acid groups is selected from the group consisting of acrylic acid or methacrylic acid.

7. A rubbery polymer as specified in anyone of claims 1 to 4, wherein the reactive cure site (co)monomer containing glycidyl groups is selected from the group consisting of glycidyl methacrylate and allyl glycidyl ether.

25

8. A rubbery polymer as specified in anyone of claims 1 to 4, wherein the reactive cure site (co)monomer containing unsaturated cure site is selected from the group consisting of dicyclopentenyl acrylate and dicyclopentenylloxyethyl methacrylate.

9. A leathery composition which is useful in automotive applications, which is comprised of (1) a thermoplastic such as PVC, halogen containing polymers, Polyurethanes, styrenic polymers (polymers which contain styrene such as
5 ABS, ASA, SEBS, etc.), Polyesters and copolymers ester-ether (COPE), Polyamides, Polycarbonates, as well as Polyolefins via compatibilization techniques, (2) a plasticizer, and (3) a rubbery polymer, which is comprised of (a) butyl acrylate, or optionally a mixture
10 of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40 percent 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of
15 alkoxy ethyl me(acrylate), (d) acrylonitrile, (e) styrene, and (f) a crosslinking agent; wherein about 1 to about 10% of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion
20 polymerization onto said rubbery polymer.

10. A polymeric blend, which is comprised of (1) a thermoplastic selected in the group comprising PVC, halogen containing polymers, Polyurethanes, styrenic
25 polymers (polymers which contain styrene such as ABS, ASA, SEBS, etc.), Polyester and copolymer ester-ether (COPE), Polyamides, Polycarbonates, as well as Polyolefins via compatibilization techniques (2) a plasticizer, and (3) a rubbery polymer which is comprised
30 of (a) butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40 percent 2-ethylhexyl acrylate, (b) at least one member

selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0% to about 40% of alkoxy ethyl me(acrylate), (d) acrylonitrile, (e)
5 styrene, and (f) a crosslinking agent; wherein about 1% to about 10% of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

10

11. A polymeric blend as specified in claim 10, wherein the polymer selected from the group consisting of halogen containing polymers is a polyvinyl chloride.

15 12. A polymeric blend as specified in claim 10, wherein the polymer selected from the group consisting of polyolefins is a high density polyethylene.

13. A polymeric blend as specified in claim 10, wherein
20 the polymer selected from the group consisting of polyolefins is a metallocene catalyzed polyolefins

14. A process for preparing a rubbery polymer which can be blended with PVC, Polyurethanes, Copolymer ester-ether
25 (COPE)as well as Polyolefins via compatibilization techniques to make leathery compositions having good heat and ultraviolet light resistance,said process comprising the steps of (1) polymerizing (a) butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl
30 acrylate containing up to about 40% 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate,

methyl acrylate, and ethyl acrylate, (c) optionally about 0% to about 40% of alkoxy ethyl me(acrylate), (d) acrylonitrile, and (e) a crosslinking agent; wherein about 1% to about 10% of a reactive cure site (co)monomer
5 containing hydroxyl groups, glycidyl groups, carboxylic acid groups or unsaturated cure site is incorporated under emulsion polymerization conditions to produce a seed polymer containing latex; (2) adding (a) styrene, (b) additional acrylonitrile, and (c) additional
10 crosslinking agent to the seed polymer containing latex under emulsion polymerization conditions which result in the formation of an emulsion containing the rubbery polymer; (3) recovering the rubbery polymer from the emulsion containing the rubbery polymer.

15

15. A process as specified in claim 14, wherein the rubbery polymer is polymerized using two-step batch, semi-continuous or continuous emulsion polymerization process.

20

16. A process as specified in claim 14, wherein in step (2) from about 4 parts by weight to about 30 parts by weight of styrene, from about 1 part by weight to about 20 parts by weight of acrylonitrile and from about 0.01
25 parts by weight to about 2 parts by weight of the crosslinking agent are added to the seed polymer per 100 parts dry weight of the seed polymer.

17. A process as specified in claim 14, wherein the
30 crosslinking agent utilized in step (1) is 1,4-butanediol dimethacrylate.

18. A process as specified in claim 14, wherein the crosslinking agent utilized in step (2) is divinylbenzene.

5 19. A process as specified in anyone of claims 14 to 18, which further comprises drying the rubbery polymer after it has been desodorized, washed and subsequently converting into powder.

10 20. A process as specified in anyone of claims 14 to 19, wherein the rubbery polymer is converted to a powder in the presence of a partitioning agent selected from the group consisting of calcium carbonate, emulsion polyvinyl chloride, and silica.

15

THIS PAGE BLANK (USPTO)

PATENT

ELIOKEM

TITLE

Rubbery polymer with improved properties

ABSTRACT

This invention discloses a rubbery polymer having improved properties which is comprised of repeat units which are comprised of (a) butyl acrylate, or optionally a mixture of butyl acrylate and 2-ethylhexyl acrylate containing up to about 40 percent 2-ethylhexyl acrylate, (b) at least one member selected from the group consisting of methyl methacrylate, ethyl methacrylate, methyl acrylate, and ethyl acrylate, (c) optionally about 0 to about 40% of alkoxy ethyl (me)acrylate, (d) acrylonitrile, (e) styrene, and (f) a crosslinking agent; wherein about 1 to about 10% of a reactive cure site (co)monomer containing hydroxyl groups, glycidyl groups, carboxylic acid groups, or unsaturated cure site is incorporated during emulsion polymerization onto said rubbery polymer.

THIS PAGE BLANK (USPTO)